


Pull-Out tests using SW8 R from 12mm STS Board

Product Code: SW8 R 4.8
 Batch Reference: Samples
 Product Description: 12mm STS Board
 Batch End Date and Time: 14/11/2019 10:20
 Operator: JU
 Temperature: 18
 Relative Humidity: 40



Notes:

Specimen Number	Yield N	Yield mm	Max Force N	Elongation at Max Force mm
1.00	903	1.15	1050	1.71
2.00	915	1.18	1140	1.75
3.00	1110	1.49	1110	1.48
4.00	1120	1.31	1120	1.30
5.00	1270	1.72	1270	1.72
6.00	1220	1.59	1290	1.87
7.00	1090	1.44	1090	1.43
8.00	15.0	0.0516	1090	1.44
9.00	1260	1.40	1260	1.40
10.00	1150	1.36	1150	1.35
Average	1010	1.27	1160	1.55
SD	371	0.461	86.9	0.199
Maximum	1270	1.72	1290	1.87
Minimum	15.0	0.0516	1050	1.30
Range	1260	1.67	242	0.571
Median	1110	1.38	1130	1.46



N.B. The results above are obtained from tests carried out in accordance with equipment conforming to BS 5427 on a random sample of fasteners. Information supplied should form part of a general guide only.

EJOT UK LTD, Hurricane Close, Sherburn Enterprise Park, Sherburn in Elmet, LEEDS LS25 6PB.

Tel. 01977 687040

www.ejot.co.uk